BANDTRANSPORT EUROPE

Bandopbouw

Type 22-84
blauw

Weefsel	
Weefsellagen	2
Weefsel bovenzijde	Polyester monofilament, breedtestabiel R
Weefsel tussenlaag	- -
Weefsel onderzijde	Polyester monofilament, breedtestabiel R

Bovenzijde			Onderzijde		
Dikte bovenzijde	0,7 mm	0,028 inch	Dikte onderzijde	0,1 mm	0,004 inch
Materiaal bovenzijde		PVC	Materiaal onderzijde		Geïmpregneerd
Profiel bovenzijde		-	Profiel onderzijde	-	
Hardheid (° ShoreA)		65			

Technische data

Wrijvingscoëfficiënt t.o.v. staal		0,2	Kracht voor 1% rek	10 N/mm	57,1 lbf/inch
Banddikte	2,4 mm	0,094 inch	Maximale bandspanning	20 N/mm	114,2 lbf/inch
Gewicht	3 kg/m²	0,61 lb/ft²	Maximale rek		2,3 %
Aanbevolen voorspanning	4-6 N/mm	22-34 lbf/inch			
Aanbevolen voorspanning rek		0,4-0,7 %			

Rol

Rolondersteuning	Ja	Minimale roldiameter buiging	40 mm	1,57 inch
Glijondersteuning	Ja	Minimum roldiameter contrabuiging	60 mm	2,36 inch
Trogondersteuning	Nee			

Internationale standaards

FDA conform	Ja	EU conform	Ja
USDA conform	Ja	ATEX conform	Nee

Eigenschappen

Olie- en vetbestendig	Ja			
Antistatische deklaag	Nee	Maximum	110 °C	230 °F
Antistatisch weefsel	Nee			
Vlamdovend	Nee			
Breedtestabiel	Ja	Minimum	-10 °C	14 °F
Kleur	blauw			



Laatste wijziging op: 23-12-2010

The information contained in this document is based on trials under standard conditions carried out by Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. New knowledge and experiences can lead to modifications and changes within a short time without prior notice. No liability whatsoever can be accepted by Bandtransport Europe B.V. with regard to the handling processing or use of the product or products concerned which much in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.