

Belt Construction

Type 22-07 white

Fabric	
Number of fabrics	2
Fabric top layer	Polyester monofilament, with lateral stability R
Fabric inner layer	-
Fabric bottom side	Polyester monofilament, with lateral stability R

Cover			Bottomside		
Thickness cover	0,1 mm	0,004 inch	Thickness bottom side	0,1 mm	0,004 inch
Material top side		Impregnated	Material bottom side		Impregnated
Profile top side		-	Profile bottom side		-
Hardness top layer (° ShoreA)		0			

Technical data

Coefficient of friction (steel)		0,2	Tension force for 1% elongation	10 N/mm	57,1 lbf/inch
Thickness	1,7 mm	0,067 inch	Maximum tension	20 N/mm	114,2 lbf/inch
Weight	2 kg/m ²	0,41 lb/ft ²	Maximum strain		2,3 %
Recommended tension	4-6 N/mm	22-34 lbf/inch			
Recommended tension: strain		0,4-0,7 %			


Rol

Carrying rollers	Yes	Minimum pulley diameter flection	20 mm	0,79 inch
Slider bed	Yes	Minimum pulley diameter contraflect	20 mm	0,79 inch
Throughed installation	No			

International standards

FDA conformance	Yes	EU conformance	No
USDA conformance	No	ATEX conformance	No

Properties

Oil and grease resistant	Yes		Maximum	110 °C	230 °F
Antistatic cover	No		Minimum	-10 °C	14 °F
Antistatic fabric	No				
Flame retardant	No				
Lateral stable	Yes				
Color	white				

Last modification on: 23-12-2010