

Belt Construction

Fabric

Number of fabrics

Fabric top layer

Polyester monofilament, with lateral stability

R

Fabric inner layer

Fabric bottom side

Polyester monofilament, with lateral stability

R

Type 22-34 black

Cover			Bottomside		
Thickness cover	0,7 mm	0,028 inch	Thickness bottom side	0,1 mm	0,004 inch
Material top side		PVC	Material bottom side		Impregnated
Profile top side		-	Profile bottom side	-	
Hardness top layer ((° ShoreA)		80			

Technical data

Coefficient of friction (steel)		0,2	Tension force for 1% elongation	10 N/mm	57,1 lbf/inch
Thickness	2,4 mm	0,094 inch	Maximum tension	20 N/mm	114,2 lbf/inch
Weight	2,9 kg/m ²	0,59 lb/ft ²	Maximum strain		2,3 %
Recommended tension	4-6 N/mm	22-34 lbf/inch			
Recommended tension: strain		0,4-0,7 %			

Rol

Carrying rollers	Yes	Minimum pulley diameter flection	40 mm	1,57 inch
Slider bed	Yes	Minimum pulley diameter contraflect	60 mm	2,36 inch
Throughed installation	No			

International standards

FDA conformance	No	EU conformance	No
USDA conformance	No	ATEX conformance	No

Properties

Limited (n
Yes Maximum 90 °C 194 °F
No state of the st
Yes Minimum -15 °C 5 °F
black
No No Yes Minimum -15 °C 5 °F

Last modification on: 23-12-2010