

Belt Construction

Fabric	
Number of fabrics	1
Fabric top layer	Polyester monofilament, with lateral
	stability
	R
Fabric inner layer	-
	-
Fabric bottom side	-
	-

Type UG12-24 white

Cover			Bottomside				
Thickness cover	0,2 mm	0,008 inch	Thickness bottom side	0,1 mm	0,004 inch		
Material top side		SPU	Material bottom side		Impregnated		
Profile top side		-	Profile bottom side	-			
Hardness top layer ((° ShoreA)		86					

Technical data

Coefficient of friction (steel)		0,2	Tension force for 1% elongation	6 N/mm	34,3 lbf/inch
Thickness	0,75 mm	0,03 inch	Maximum tension	10 N/mm	57,1 lbf/inch
Weight	0,75 kg/m ²	0,15 lb/ft²	Maximum strain		2,2 %
Recommended tension	2-4 N/mm	11-22 lbf/inch			
Recommended tension: strain		0,4-0,7 %			

Rol

Carrying rollers	Yes	Minimum pulley diameter flection	10 mm	0,39 inch
Slider bed	Yes	Minimum pulley diameter contraflect	20 mm	0,79 inch
Throughed installation	No			

International standards

FDA conformance	Yes	EU conformance	Yes
USDA conformance	Yes	ATEX conformance	No

Properties

Oil and grease resistant	Yes	°c ∩			
Antistatic cover	No	IX- K-	Maximum	100 °C	212 °F
Antistatic fabric	No	X- K-			
Flame retardant	No	x. X.			
Lateral stable	Yes	't- (-	Minimum	-40 °C	-40 °F
Color	white				

Last modification on: 23-12-2010