

**Belt Construction****Type 22-16/3W
green**

Fabric	
Number of fabrics	2
Fabric top layer	Polyester monofilament, with lateral stability, light RL
Fabric inner layer	-
Fabric bottom side	Polyester monofilament, with lateral stability, antistatic, low noise RXA

Cover			Bottomside		
Thickness cover	1,9 mm	0,075 inch	Thickness bottom side	0 mm	0 inch
Material top side		PVC	Material bottom side		Fabric
Profile top side		Wavegrip	Profile bottom side		-
Hardness top layer (° ShoreA)		50			

Technical data

Coefficient of friction (steel)		0,18	Tension force for 1% elongation	11 N/mm	62,8 lbf/inch
Thickness	5,1 mm	0,201 inch	Maximum tension	20 N/mm	114,2 lbf/inch
Weight	4,4 kg/m ²	0,9 lb/ft ²	Maximum strain		2,1 %
Recommended tension	5-7 N/mm	28-39 lbf/inch			
Recommended tension: strain		0,4-0,7 %			


Rol

Carrying rollers	Yes	Minimum pulley diameter flection	40 mm	3,15 inch
Slider bed	Yes	Minimum pulley diameter contraflect	60 mm	5,51 inch
Throughed installation	No			

International standards

FDA conformance	No	EU conformance	No
USDA conformance	No	ATEX conformance	No

Properties

Oil and grease resistant	Limited		Maximum	80 °C	176 °F
Antistatic cover	No		Minimum	-20 °C	-4 °F
Antistatic fabric	Yes				
Flame retardant	No				
Lateral stable	Yes				
Color	green				

Joint data for hot press

Pressure	1,5 Bar	Temperature presselement topside	170 °C	338 °F
		Temperature presselement bottomside	185 °C	365 °F
		Temperature thermocouple	165 °C	329 °F

Last modification on: 23-12-2010

The information contained in this document is based on trials under standard conditions carried out by Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. New knowledge and experiences can lead to modifications and changes within a short time without



BANDTRANSPORT EUROPE

prior notice. No liability whatsoever can be accepted by Bandtransport Europe B.V. with regard to the handling processing or use of the product or products concerned which much in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.